

## Q8 Auto D VI

*Synthetic automatic transmission fluid for GM Dexron VI*

### Description

Q8 Auto D VI is a superior low viscosity multi-vehicle automatic transmission fluid for step-type transmissions. This product has set new standards in cold temperature fluidity and fluid robustness. It offers 50% extended drain interval (240.000 km vs 160.000 km for a standard Dexron III H oil) and exceptional shear, friction and oxidation stability, film strength and wear control.

### Applications

Q8 Auto D VI is recommended for 99% of all modern passenger car automatic transmissions. It meets the requirements of Volvo 97342, ZF Lifeguardfluid 5, 6 and 8, and GM Dexron VI, and exceeds the Aisin Warner JWS 3309 (T-IV) & JWS 3324 (WS), AW-1. Q8 Auto D VI is also backwards compatible with all previous Dexron specified fluid applications.

### Benefits

- Superior protection against wear and extends component life.
- Optimal friction characteristics even at low temperatures
- Outstanding elastomer compatibility
- Excellent oxidation and thermal stability

### Specifications, recommendations and approvals

<b>Aisin Warner</b>	JWS 3309	<b>MB</b>	236.12
<b>Aisin Warner</b>	JWS 3324	<b>MB</b>	236.14
<b>Aisin Warner</b>	JWS AW-1	<b>MB</b>	236.15
<b>BMW/MINI</b>	7045E	<b>MB</b>	236.17
<b>BMW/MINI</b>	ETL 8072B	<b>MB</b>	236.41
<b>BMW/MINI</b>	LT71141 (ZF 5HP 18FL/19FL/24A)	<b>Mitsubishi</b>	Diaqueen SP-IV
<b>GM</b>	<b>Dexron VI</b>	<b>VAG</b>	VW G 052 162
<b>Hyundai/Kia</b>	SPH-IV	<b>VAG</b>	VW G 055 162
<b>Isuzu</b>	Besco ATF SP	<b>VAG</b>	VW G 060 162
<b>JASO</b>	M315 Type 1A LV	<b>Volvo</b>	97342 (AT 102)
<b>JASO</b>	M315 Type 2A		

*Color code blue = officially approved*

### Properties

	Method	Unit	Typical
Density, 15 °C	D 4052	g/ml	0,847
Kinematic Viscosity, 40 °C	D 445	mm <sup>2</sup> /s	29,8
Kinematic Viscosity, 100 °C	D 445	mm <sup>2</sup> /s	6,0
Viscosity Index	D 2270	-	151
Brookfield Viscosity, -40 °C	D 2983	Pa.s	12
Pour Point	D 97	°C	-54
Flash Point, COC	D 92	°C	> 200

The figures above are not a specification. They are typical figures obtained within production tolerances.

### Remarks

Product Data Sheet includes a selection of specifications, for full overview please consult the Q8Oils website.