

Q8 Verdi 32

Multi-purpose circulating oil

Description

Q8 Verdi 32 is an advanced multi-purpose circulating oil with a long service life. It has a high chemical and thermal stability and protects against rust and corrosion. Q8 Verdi 32 has optimum lubricating characteristics and water resistant properties.

Applications

Q8 Verdi 32 is used in hydro turbines, pumps, valves and other applications that require a long service life. It is applied in a variety of industrial systems that don't need anti-wear performance. Q8 Verdi 32 is highly recommended for plain and rolling bearings, vacuum pumps, hydraulic pumps and air compressor applications.

Benefits

Extensive lubricant applications so limited products needed

Extends service life time thus minimal costs and maximal efficiency

Features

Highly suitable for a wide range of application

Outstanding oxidation stability

Optimum anti-corrosion characteristics

Optimum separation of water

Specifications & Approvals

| | | | |
|-----|--------------|-----|------------|
| DIN | 51506 VBL | DIN | 51524-1 HL |
| DIN | 51515-1 L-TD | ISO | 6743-2 F |
| DIN | 51517-2 CL | | |

Properties

| | Method | Unit | Typical |
|------------------------------------|--------|--------------------|------------|
| ISO Viscosity Grade | - | - | 32 |
| Density, 15 °C | D 4052 | g/ml | 0,87 |
| Kinematic Viscosity, 40 °C | D 445 | mm ² /s | 32.0 |
| Kinematic Viscosity, 100 °C | D 445 | mm ² /s | 5.33 |
| Viscosity Index | D 2270 | - | 98 |
| Total Acid Number | D 974 | mg KOH/g | 0.12 |
| Pour Point | D 97 | °C | -30 |
| Flash Point, COC | D 92 | °C | 208 |
| Colour | D 1500 | - | L 1.0 |
| Air Release, 50 °C | D 3427 | min | 4 |
| Emulsion, Distilled Water, 82.2 °C | D 1401 | - | 40-40-0(5) |
| Foam, 5 min blowing, seq. 1-2-3 | D 892 | ml | 10/20/10 |
| Foam, 10 min settling, seq. 1-2-3 | D 892 | ml | 0/0/0 |
| Rust Test, Proc. A and B, 24 h | D 665 | - | pass |
| Copper Strip, 3 h, 100 °C | D 130 | - | 1 |

The figures above are not a specification. They are typical figures obtained within production tolerances.